United	States	Patent	[19]
--------	--------	--------	------

Ruffner et al.

[11] Patent Number:

4,600,761

[45] Date of Patent:

Jul. 15, 1986

[54]	ACRYLIC EMULSION COPOLYMERS FOR
	THICKENING AQUEOUS SYSTEMS AND
	COPOLYMERIZABLE SURFACTANT
	MONOMERS FOR USE THEREIN

[75] Inventors: Charles G. Ruffner; John M.

Wilkerson, III, both of Hamilton

County, Tenn.

[73] Assignee: Alco Chemical Corporation,

Chattanooga, Tenn.

[21] Appl. No.: 782,571

[22] Filed: Oct. 1, 1985

Related U.S. Application Data

[63]	Continuation-in-part of Ser. No. 719,768, Apr. 4, 1985.
------	---

		C08F 216/14
[52]	U.S. Cl	526/270 ; 526/301;

524/555; 524/549; 549/476 [58] Field of Search 526/270, 301, 302; 524/555

[56] References Cited

U.S. PATENT DOCUMENTS

C.S. TATENT DOCUMENTS						
		Bortnick .	•			
4,233,425	11/1980	Tefertiller et al				
4,351,754	9/1982	Dupre .				
		Sonnabend .				
4,421,902	12/1983	Chang et al				
4,507,188	3/1985	Chu	204/159.23			
4,514,552	4/1985	Shay et al				

OTHER PUBLICATIONS

Specialty Chemicals Developmental Products Techni-

cal Data-Developmental Monomer XAS-10743.00 Isocyanatoethyl Methacrylate, The Dow Chemical Co. (1983).

IEM Isocyanatoethyl Methacrylate A New Difunctional Monomer-Properties, Applications, and Safe Handling, The Dow Chemical Co. (1984).

Paul E. Cranley "Isocyanatoethyl Methacrylate: A Latent Crosslinker for Coating and Adhesive Resins:, The Dow Chemical Co. (1983).

IEM Dual Functional Monomer, The Dow Chemical Co. (1983).

Research Disclosure 20816 (Aug. 1981).

Primary Examiner—Paul R. Michl Attorney, Agent, or Firm—Howson and Howson

[57] ABSTRACT

Acrylic emulsion copolymers are prepared by emulsion polymerization of (A) a surfactant monomer, (B) an α , β -ethylenically unsaturated carboxylic acid monomer, (C) a nonionic α , β -ethylenically unsaturated monomer and (D) optionally a polyethylenically unsaturated cross-linking monomer. The surfactant monomer is prepared by condensing a polyhydric alcohol or primary amine-containing nonionic surfactant with a monoethylenically unsaturated monoisocyanate. At a low pH the copolymer may be in the form of an aqueous dispersion or latex, but thickens upon neutralization of at least some of the carboxyl groups.

26 Claims, No Drawings